

CA-41 HF Properties

Mechanical	Test method	Units	CA-41 HF
Tensile Strength	ASTM D638	psi	7680
Elongation	ASTM D638	%	2.4
Modulus of Elasticity	ASTM D638	psi	395500
Flexural Strength	ASTM D790	psi	11050
Flexural Modulus	ASTM D790	psi	-
Impact Strength – Izod (Notched)	ASTM D256	ft-lb/in	0.3
Impact Strength – Falling Weight (1/8")	ASTM D5420 GB	in-lb	2
Rockwell Hardness	ASTM D785	M scale	74

Thermal	Test method	Units	CA-41 HF
Vicat Softening Temperature	ASTM D1525	°F	192
Heat Deflection Temperature Under Load (264 psi)	ASTM D648	°F	160
Melt Flow Rate	ASTM D1238	g/10 min	34
Coefficient of Linear Thermal Expansion (-30 to 30°C)	ASTM D696	mm/(mm-oC)	6 X 10 ⁻⁵
Molding Shrinkage	ASTM D955	%	0.2-0.6

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.