

TUFFAK SL-R POLYCARBONATE SHEET

UV RESISTANT SIGN GRADE

TUFFAK SL-R Sign Grade sheet -R (Renewable) sheet is a transparent polycarbonate sheet product with up to 90% post-industrial recycled content, and is the ideal option where recycled sheet is preferred or specified. It has an advanced UV resistance technology that promotes long lasting outdoor weathering performance. It features outstanding impact strength, excellent dimensional stability, high temperature resistance, and high clarity. This lightweight thermoformable sheet is also easy to fabricate and decorate. TUFFAK SL-R is offered in clear, a wide range of standard sign colors, or can be custom matched to any color. The product, available in either sheet or reels, has a proven track record of outstanding performance in extreme environments and meets the UL 879 standard for electric sign components. A ten (10) year limited product warranty is available for both clear and colors for breakage resistance. Clear sheet is also covered for weathering resistance. The terms of the warranty are available upon request.

APPLICATIONS

Flat and formed sign faces and channel letters, LEED certified

Regulatory code compliance and certifications

Florida Building Code 2017
High Velocity Hurricane Zone Classified
Miami-Dade NOA: NOA

UL 879: Electric Sign Components,
UL File #E146154

UL 94: Flammability File #E87887


UL 746C: Suitability for Outdoor Use,
UL File #E87887

UL 972: Burglary Resistant Glazing
Materials, UL File #BP2126


TYPICAL PROPERTIES

Property	Test Method	Units	Values
PHYSICAL			
Specific Gravity	ASTM D792	-	1.2
Refractive Index	ASTM D542	-	1.586
Light Transmission, Clear @ 0.118"	ASTM D1003	%	86
Light Transmission, B54 White @ 0.118"	ASTM D1003	%	27
Light Transmission, B54 White @ 0.150" and 0.177"	ASTM D1003	%	27
Light Transmission, B72 White, All gauges	ASTM D1003	%	72
Water Absorption, 24 hours	ASTM D570	%	0.15
Poisson's Ratio	ASTM E132	-	0.38
MECHANICAL			
Tensile Strength, Ultimate	ASTM D638	psi	9,500
Tensile Strength, Yield	ASTM D638	psi	9,000
Tensile Modulus	ASTM D638	psi	340,000
Elongation	ASTM D638	%	110
Flexural Strength	ASTM D790	psi	13,500
Flexural Modulus	ASTM D790	psi	345,000
Compressive Strength	ASTM D695	psi	12,500
Compressive Modulus	ASTM D695	psi	345,000
Izod Impact Strength, Notched @ 0.125"	ASTM D256	ft-lbs/in	18
Izod Impact Strength, Unnotched @ 0.125"	ASTM D256	ft-lbs/in	60 (no break)
Instrumented Impact @ 0.125"	ASTM D3763	ft-lbs	47
Shear Strength, Ultimate	ASTM D732	psi	10,000
Shear Strength, Yield	ASTM D732	psi	6,000
Shear Modulus	ASTM D732	psi	114,000
Rockwell Hardness	ASTM D785	-	M70 / R118
THERMAL			
Coefficient of Thermal Expansion	ASTM D696	in/in/°F	3.75 x 10 ⁻⁵
Coefficient of Thermal Conductivity	ASTM C177	BTU-in/hr-ft ² -°F	1.35
Heat Deflection Temperature @ 264 psi	ASTM D648	°F	270
Heat Deflection Temperature @ 66 psi	ASTM D648	°F	280
Brittleness Temperature	ASTM D746	°F	-200
ELECTRICAL			
Dielectric Constant @ 10 Hz	ASTM D150	-	2.96
Dielectric Constant @ 60 Hz	ASTM D150	-	3.17
Volume Resistivity	ASTM D257	Ohm-cm	8.2 x 10 ¹⁶
Dissipation Factor @ 60 Hz	ASTM D150	-	0.0009
Arc Resistance	-	-	-
Stainless Steel Strip electrode	ASTM D495	Seconds	10
Tungsten Electrodes	ASTM D495	Seconds	120
Dielectric Strength, in air @ 0.125"	ASTM D149	V/mil	380
FLAMMABILITY			
Horizontal Burn, AEB	ASTM D635	in.	<1
Flame Class @ 0.060"	UL 94	-	HB
Ignition Temperature, Self	ASTM D1929	°F	1022
Ignition Temperature, Flash	ASTM D1929	°F	824

TUFFAK SL-R POLYCARBONATE SHEET



*Instrumented Impact per ASTM D 3763, sample thickness 0.125" nominal



Visible yellowness at 8 or greater

*Based upon xenon WOM accelerated weathering for UV dose at mid-latitude location

TUFFAK SL Standard Colors

Standard Plaskolite Color	Standard Industry Color	Standard Gauge
White/ B59 - B54	7328	0.093" - 0.236"
Red/ D96	2283	0.118" - 0.177"
Red/ D99	2793	0.118" - 0.177"
Blue/ F84	2114	0.118" - 0.177"
Blue/ F85	2051	0.118" - 0.177"
Green/ H87	2108	0.118" - 0.177"
Yellow/ M72	2037	0.118" - 0.177"
Orange/ C59	2119	0.118" - 0.177"

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.

© 20223PLASKOLITE, LLC 032023
TUFFAK* is a registered trademark of Plaskolite LLC

PLASKOLITE

400 W Nationwide Blvd, Suite 400
Columbus, OH 43215
800.848.9124 • Fax: 877.538.0754
plaskolite@plaskolite.com
www.plaskolite.com

PDS451_TUF_SLR