

# OPTIX CA-924 CLEAR

OPTIX CA-924 is a medium flow and medium impact-resistant acrylic polymer designed for injection molding. OPTIX CA-924 is an impact-resistant grade that maintains excellent optical and weather resistant properties.

## APPLICATIONS

Automotive parts, taillight lenses, instrument panel lenses, sun visors, road reflectors, industrial sight gauges, and faucet handles

### TYPICAL PROPERTIES\*

Property	Test Method	Units	Values
<b>OPTICAL</b>			
Luminous Transmittance	ASTM D1003	%	92.0
Haze	ASTM D1003	%	< 2.0
Refractive Index	ASTM D542	-	1.49
<b>RHEOLOGICAL</b>			
Melt Flow Rate (230°C/3.8kg)	ASTM D1238	g/10 min	6.3
<b>MECHANICAL</b>			
Tensile Strength	ASTM D638	psi (MPa)	8,500 (59)
Tensile Elongation	ASTM D638	%	5.0
Tensile Modulus of Elasticity	ASTM D638	psi (MPa)	320,000 (2,200)
Flexural Strength	ASTM D790	psi (MPa)	12,500 (86)
Flexural Modulus	ASTM D790	psi (MPa)	330,000 (2,300)
Impact Strength - Notched Izod (1/4")	ASTM D256	ft-lbf/in. (J/m)	0.6 (32)
Impact Strength - Falling Dart (GB, 1/8")	ASTM D5420	in.-lbf (J)	20 (2.3)
Rockwell Hardness (M Scale)	ASTM D785	-	76
<b>THERMAL</b>			
Vicat Softening Temperature (50N, 50°C/hr)	ASTM D1525	°F (°C)	207 (97)
Heat Deflection Temperature Under Load (264 psi)	ASTM D648	°F (°C)	187 (86)
Coefficient of Linear Thermal Expansion	ASTM D696	cm/(cm·°C)	7 × 10 <sup>-5</sup>
Mold Shrinkage	ASTM D955	%	0.2 - 0.6
<b>OTHER</b>			
Specific Gravity	ASTM D792	-	1.17
Flammability Class	UL 94	-	HB
Water Absorption	ASTM D570	%	0.3
3-year Outdoor Weathering	SAE J576 (AMECA)	-	Listed
ASTM Classification	ASTM D788	-	0221V4

\* Typical Properties are not intended for specification purposes

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determines the suitability of our materials and suggestions before adopting them on a commercial scale.