

FABBACK AR Coated Acrylic Mirror Sheet

Typical Properties

Mechanical	TEST METHOD	UNITS	AR Coated Sheet
Abrasion Resistance - Change in Haze - 100 cycles	ASTM D1044	Haze, %	<5
Steel Wool Rotary Test 12 & 15 psi / 5 revolutions		Haze %	<1

These suggestions and data are based on information we believe to be reliable. They are offered in good faith, but without guarantee, as conditions and methods of use are beyond our control. We recommend that the prospective user determine the suitability of our materials and suggestions before adopting them on a commercial scale.

Questions? Please contact Plaskolite Customer Support 800-848-9124